

Technical Data Sheet



DIRECTIONS FOR USE

SHAKE CAN FOR AT LEAST TWO MINUTES BEFORE USE Prepare the area to be painted, ensuring it to be free from dirt, wax, oil, etc. Lightly abrade the surface, mask off with masking paper and masking tape to prevent any overspray. Use between 15°C to 25°C in a well ventilated area. Shake can vigorously for at least two minutes to ensure the primer is thoroughly mixed. Repeat shaking at regular intervals during use. Spray from a distance of 20cm to 25cm. Apply several light coats with up to 10 minutes intervals between coats to achieve the best results. The number of coats depends on the colour that is being over painted. Sandable after approx 30 minutes at 20°C. After use invert can and spray to clear the valve and sprayhead, this prevents the aerosol from clogging up prior to using next time.

PART NUMBERS

Cumbria

325052 High Build & Etch Black 325053 High Build & Etch White 325051 High Build & Etch Light Grey 325351 High Build & Etch Dark Grey

This information is provided in good faith based upon data and sources believed to be reliable and correct. Conditions of use, outside the control of the Company, dictate that no responsability can be assumed for the ultimate performance of this product.

Cumbrian Marketing Ltd Townfoot Industrial Estate Brampton CA8 1SW

Phone: (+44) 0169 7741 080 Email: hbcmeister@cumbrian.co.uk www.hbcmeister.co.uk



F

R

S